



ENGLISH

ADETAC S

EXTRA STRENGTH FAST ACRYLIC ADHESIVE

Suitable for gluing floors and coverings in homogeneous PVC: wall-to-wall carpeting and non-woven needle-punched carpeting, floor coverings with foam rubber backing, jute and linoleum canvas.



ADHESIVE FOR CARPETING
AND RESILIENT TEXTILE
FLOORS

HOW TO USE:

PREPARATION OF THE SURFACE

Always check the humidity of the foundation and of the wood with appropriate instruments. The humidity of the substrate should be measured in depth (approx. 2–3 cm) using a carbide hygrometer in order to rule out the presence of strongly hygroscopic substances (such as pumice, vermiculite) which can release large quantities of trapped humidity which results in the swelling of the flooring. Do not apply on subfloors that are not protected from swelling due to humidity (always insulate with an adequate steam sealed lining). Thin or dust-producing subfloors must be consolidated with our PRIMER K31 that ensures perfect bonding of the adhesive to the surface (see the technical data sheet). Do not apply to floors in rooms that do not have windows or doors. Do not apply to floors if the walls or ceiling of the room are not perfectly dry.

APPLICATION

Make sure the product is at ambient temperature before use. Apply adhesive only to the subfloor with an appropriate toothed spatula, wait a couple minutes (depending on the strength of the laying surface and ambient climatic conditions) for the adhesive to dry partially which must be as dry as possible but still able to wet the underside of the covering. Apply the covering using uniform pressure over the entire surface in order to expel any air bubbles and ensure perfect contact. Before bonding always check that the humidity of the subfloor is less than 2% (<0.5% anhydrite). Ambient temperature between 15 and 25°C, relative humidity not superior to 75%. Always use adequate personal protective equipment. Always consult the MSDS sheet of the product.



ADESIV



The company complies to quality management system standard UNI EN ISO – 9001:2008 certified by SGS Italia S.p.A., certificate no. IT07/0491.

TECHNICAL DATA (at standard conditions):

Aspect:	Paste
Viscosity (@20°C; Brookfield):	40000
Dryness (%):	65 - 70
Coverage (g/m ²):	300 - 400
Pot life (minutes):	15 - 25
Application temperature (°C):	+15 - +25
Days required before walking o	3 - 4 (depending on ambient temperature)
Application/Tools:	thin-toothed spatula
Tool cleaning:	Water, when the product is still fresh
Storage (months): <i>temperature between +5°C and +25°C</i>	6
Information on disposal	Dispose of product in accordance with local and national laws
Packaging	5 kg or 25 kg pails
Limitations of use:	Do not apply in damp areas Absolutely avoid freezing temperatures. Rigid materials, especially during winter time, must be laid in the areas where they will be used and left to rest to avoid deformation due to storage Make sure the temperature of the product is 20°C before applying Always use adequate personal protective equipment

NOTES

ADESIV srl Guarantees that the information in the present sheet are given to the best of its experience and technical-scientific knowledge; however, it is not liable for results obtained as application conditions are out of its control. It is recommended to always verify the suitability of the product for the specific case. The present sheet annuls and substitutes any previous sheet.



The company complies to quality management system standard UNI EN ISO - 9001:2008 certified by SGS Italia S.p.A., certificate no. IT07/0491.