



ENGLISH

## PELPREN PL6-G

BICOMPONENT WATER FREE ADHESIVE FOR RUBBER AND PVC  
Single application product specific for rubber floors, sports floors in rubber conglomerates, PVC , inside or outside any kind of subfloor, even non-absorbing ones.

### HOW TO USE:

#### PREPARATION OF THE SURFACE

Always check the subfloor with appropriate instruments. The humidity of the substrate should be measured in depth (approx. 2-3 cm) using a carbide hygrometer in order to rule out the presence of strongly hygroscopic substances (such as pumice, vermiculite) which can release large quantities of trapped humidity with a resulting swelling of the flooring. Do not apply on subfloors which are not protected from possible swelling due to humidity (always insulate with an adequate steam sealed lining). Thin or dust-producing subfloors must be consolidated with our PRIMERS (PA 400, PA 35, WB PU), that ensure perfect bonding of the adhesive to the surface (see the technical data sheet). Do not apply to floors in rooms that do not have windows or doors. Do not apply to floors if the walls or ceiling of the room are not perfectly dry. Do not apply on bituminous surfaces oil transudation may occur.

#### APPLICATION

Make sure the product is at ambient temperature before use. Pour PELPREN PL6-G component (B) into the container of PELPREN PL6-G component (A) mixing it well with electric mixer to obtain a homogeneous and uniform paste. The paste thus obtained is to be applied with an appropriate fine-tooth spatula n. 4 on the subfloor that must be compact, dry, clean, free from any detaching parts such as residues of wall paints, dust, wax or similar. The product is not to be diluted. Before gluing, always check that the subfloor humidity is <2% (<0.5% anhydrite). Ambient temperature from 15 to 25°C, relative humidity not greater than 75%. Always use adequate personal protective equipment. Always consult the MSDS sheet of the product.



ADHESIVE FOR CARPETING  
AND RESILIENT TEXTILE  
FLOORS

**ADESIV**



The company complies to quality management system standard UNI EN ISO - 9001:2008 certified by SGS Italia S.p.A., certificate no. IT07/0491.

## NOTE

Do not use PELPREN PL6-G in laying especially thin flooring where adhesive stripes may show through. Rigid materials, especially in the winter season, must be laid out in the rooms where they are to be installed and allowed to stand in order to avoid warping due to storage.



The company complies to quality management system standard UNI EN ISO – 9001:2008 certified by SGS Italia S.p.A., certificate no. IT07/0491.

## TECHNICAL DATA (at standard conditions):

Aspect:	Paste
Viscosity (@20°C; Brookfield):	70000 - 90000
Approximate coverage (g/m <sup>2</sup> ):	600 - 700
Pot life (minutes):	90 - 120
Application temperature (°C):	+15 - +25
Hours required before walking	4 - 5
Application/Tools:	Fine-tooth spatula n.4
Tool cleaning:	GR7, when the product is still fresh
Removal of product:	PULITORE LS, when the product is still fresh
Storage (months): <i>temperature between +5°C and +25°C</i>	12
Information on disposal	Dispose of product in accordance with local and national laws
Packaging	10 kg unit(9 kg component A + 1 kg component B)
Limitations of use:	Do not apply in damp areas Always use adequate personal protective equipment Aerate area during application avoiding draughts Make sure the temperature of the product is 20°C before applying

## NOTES

ADESIV srl Guarantees that the information in the present sheet are given to the best of its experience and technical-scientific knowledge; however, it is not liable for results obtained as application conditions are out of its control. It is recommended to always verify the suitability of the product for the specific case. The present sheet annuls and substitutes any previous sheet.



The company complies to quality management system standard UNI EN ISO - 9001:2008 certified by SGS Italia S.p.A., certificate no. IT07/0491.