



iQ Toro SC - 3093107



3093 100  
3094 100



3093 101  
3094 101



3093 102  
3094 102



3093 103  
3094 103




3093 104  
3094 104



3093 105  
3094 105



3093 107  
3094 107



3093 570  
3094 570



3093 572  
3094 572




3093 573  
3094 573



3093 574  
3094 574



3093 575  
3094 575



3093 578  
3094 578

TECHNICAL DATA	STANDARDS	iQ Toro SC	
<b>Classification</b>			
<b>Classification</b>	ISO 10582 (EN 649) - vinyl	Permanently static conductive pressed homogeneous vinyl flooring	
	ISO 10581 (EN 649) - vinyl ISO 10874 (EN 685) - linoleum domestic commercial light industrial	Classes: - 34 43	
	UPEC Classification NF UPEC certificate number (Ref NF189)	U4 P3 E2/3 C2 312-016.1	
<b>Characteristics</b>			
<b>Wear layer thickness</b>	ISO 24340 (EN 429)	2.00mm	
<b>Total thickness</b>	ISO 24346 (EN 428)	2.00mm	
<b>Total weight</b>	ISO 23997 (EN 430)	2 950g/m <sup>2</sup>	
<b>Surface Treatment</b>		iQ Pur	
<b>Flexibility</b>	ISO 23344 (EN 435 Method A)	Pass	
<b>Technical performances</b>			
<b>Residual indentation</b>	Average measured value	0.02mm	
	ISO 24343-1 (EN 433) requirement	≤ 0.10mm	
<b>Reaction to fire</b>	EN 13501-1 EN ISO 9239-1 EN ISO 11925-2	B <sub>s</sub> s1 ≥ 8 kW/m <sup>2</sup> Pass	
	<b>Slip resistance</b>	DIN 51130 EN 13893	R9 ≥ 0.3
	<b>Dimensional stability</b>	ISO 23999 (EN 434)	≤ 0.40% for rolls ≤ 0.25% for tiles
<b>Castor chair test</b>	ISO 4918 (EN 425)	Suitable	
<b>Thermal resistance Underfloor heating</b>	EN ISO 10456 (EN 12524)	0.01m <sup>2</sup> K/W Suitable	
<b>Thermal resistance</b>	DIN 52612/EN 12667	Approx. 0.01m <sup>2</sup> K/W	
<b>Light fastness</b>	EN ISO 105-B02	≥ level 6	
<b>Abrasion group Volume loss</b>	EN 660: Part 2	Group P: ≤ 4.0mm <sup>3</sup>	
<b>Electrical insulation</b>	VDE 100, Part 600	R <sub>i</sub> ≤ 5 x 10 <sup>4</sup> ohms	
<b>Static electrical charge</b>	EN 1815	< 2kV	
<b>Electrical resistance</b>	ESD-approval SP-method 2472 EN 1081	R ≤ 10 <sup>8</sup> ohms R <sub>1</sub> 5 x 10 <sup>4</sup> ≤ R ≤ 10 <sup>6</sup> ohms R <sub>2</sub> 5 x 10 <sup>4</sup> ≤ R ≤ 10 <sup>6</sup> ohms 5 x 10 <sup>4</sup> ≤ R ≤ 10 <sup>6</sup> ohms ≤ 3.5 x 10 <sup>7</sup> ohms	
	EN/IEC 61340-4-1 EN/IEC 61340-4-5		
<b>Chemical resistance</b>	ISO 26987 (EN 423)	Good resistance	
<b>Fungi and bacteria resistance</b>	DIN EN 846 part C	Does not favour growth	
<b>Underfloor heating</b>	—	Suitable - max 27°C	

The above information is subject to modifications for the benefit of further improvement (05/2014).  
For more detailed technical information, please contact Tarkett.



3093 576  
3094 576

## Main Product Features

- 14 colours available both in sheets and tiles
- Colour coordinated with iQ Granit
- $5 \times 10^4 \leq R \leq 10^6$  ohms
- Unique patented conductive iQ PUR

## Surface Treatment



## Sustainability Tag



## Logistics Information


Available in rolls  
Rolls length: 231m

Laying direction:



Available in tiles

Laying direction:



## General Information



Play with the Room Designer