

TECHNICAL CHARACTERISTICS

wineo 550 / 550 digital

Laminate flooring with an ESH Lacquering acc. to EN 14978

wineo

	wineo 550 matt / high gloss	
Format	853 x 331 mm	
Product thickness	8 mm	
Panels / m ² per box	8 / 2.26 m ²	
Boxes / m ² per pallet	45 / 101.70 m ²	
Guarantee	20 years – Guarantee for private use according to Windmüller warranty conditions – www.wineo.de	

Classification		Product composition
Utilization class 23 EN ISO 10874	Heavy-duty use in the domestic area	1 Surface texture matt and high gloss finishes
Utilization class 32 EN ISO 10874	Normal use in the commercial sector	2 Wear layer Top coat
AC4 Abrasion resistance EN 13329, annex E (matt) EN 15468, annex A (high gloss)	AC4	3 Decor Decor varnish
Impact resistance EN 13329, annex H	Small-diameter ball test ≥ 12 N Large-diameter ball test ≥ 750 mm	4 Core board Aqua-Protect®
Resistance to staining EN 438	Group 1 + 2: grade 5 Group 3: grade 4	5 Profile connection LocTec® locking system
Light fastness EN ISO 105-B02	Light fastness (method 2) ≥ 6	6 Profile seal
Residual indentation EN ISO 24343-1	Residual indentation ≤ 0.05 mm	7 Backing Kraft paper
Effect of a furniture leg EN 424	Foot type 0 - no visible change	
Castor chair test EN 425	25000 revolutions no damage with rolls type W	
Thermal resistance EN 12667	0.06 (m ² K)/W without insulation mat 0.07 (m ² K)/W with insulation mat soundPROTECT	
REACH	free from SVHC substances ≥ 0.1 %	
Disposal	<u>Private:</u> like laminated furniture; possible with normal domestic refuse <u>Commercial:</u> Refuse-key-no. AVV 170201	

Windmüller GmbH
Nord-West-Ring 21
D-32832 Augustdorf

DOP: 1601010
EN 14041:2004 / AC2006
1658

- 18 -

$\geq 0,10$ W/(mK)

www.wineo.de

ÉMISSIONS DANS L'AIR INTÉRIEUR*

A+

A+ A B C

Information représentative des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité par inhalation, sur une échelle de classe allant de C (fortes émissions) à A+ (très faibles émissions)

- Relevant Information:**
- Underfloor heating: In conjunction with suitable underlay material (soundPROTECT or equivalent) suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperature of 27° C.
 - Cleaning and care: see separate cleaning & care instruction.
 - No approval for gluing over the whole area without an integrated insulation mat.
Gluing over the whole area with an integrated insulation mat only after consultation with the application technology department at Windmüller GmbH.
 - Technical subjects can be changed by Windmüller GmbH.